

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 568 721 A1**

(12) **EUROPEAN PATENT APPLICATION**  
published in accordance with Art. 158(3) EPC

(43) Date of publication:  
31.08.2005 Bulletin 2005/35

(51) Int Cl.7: **C08F 220/22**, C09D 133/16,  
C04B 41/64

(21) Application number: **03810642.3**

(86) International application number:  
**PCT/JP2003/014184**

(22) Date of filing: **07.11.2003**

(87) International publication number:  
**WO 2004/041880 (21.05.2004 Gazette 2004/21)**

(84) Designated Contracting States:  
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR**  
**HU IE IT LI LU MC NL PT RO SE SI SK TR**  
Designated Extension States:  
**AL LT LV MK**

(72) Inventors:  
• **FUKUDA, Teruyuki,**  
**Yodogawa Works of Daikin In. Ltd**  
**Settsu-shi, Osaka 566-8585 (JP)**  
• **MAEDA, Masahiko,**  
**Yodogawa Works of Daikin In. Ltd.**  
**Settsu-shi, Osaka 566-8585 (JP)**

(30) Priority: **08.11.2002 JP 2002324993**

(71) Applicant: **DAIKIN INDUSTRIES, LTD.**  
**Osaka 530-8323 (JP)**

(74) Representative: **HOFFMANN EITLE**  
**Patent- und Rechtsanwälte**  
**Arabellastrasse 4**  
**81925 München (DE)**

(54) **TREATING AGENT FOR MASONRY**

(57) The application to a masonry of a fluorine-containing polymer comprising (1) a fluoroalkyl group-containing monomer, and (2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the

polymer, can give a masonry having excellent water- and oil-repellency and soil resistance.

EP 1 568 721 A1

## Description

### Technical Field

5 [0001] The present invention relates to a polymer for treating a masonry and a method of treating a masonry. A masonry of the present invention has high water- and oil-repellency and soil resistance.

### Background Arts

10 [0002] It is studied that water and oil repellency and soil resistance are imparted by treating a surface of a masonry such as stone with a compound having a fluoroalkyl group (Rf group).

[0003] For example, JP-A-57-23662 describes that an acrylate having a Rf group is coated on a concrete and a stone to form a protective film. JP-A-11-077677 proposes that a stone is treated with a phosphate ester having a Rf group. JP-A-07-109317 discloses a treatment agent comprising a fluorine-containing polymer comprising a monomer  
15 having a Rf group, and 0.1 to 1.9 % by weight, based on the polymer, of a silicone-based vinyl monomer. These treatment agents, however, have sufficient oil repellency but insufficient water repellency, or sufficient water repellency but insufficient oil repellency.

### Disclosure of Invention

20 [0004] One of objects of the present invention is to provide a treatment agent which imparts both water repellency and oil repellency.

[0005] The other of objects of the present invention is to provide a polymer for treating a masonry, which is soluble in an organic solvent (particularly a petroleum solvent) having high flash point (for example, at least 65°C).

25 [0006] The present invention provides a fluorine-containing polymer for treating a masonry, comprising:

- (1) a fluoroalkyl group-containing monomer, and
- (2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the polymer.

30 [0007] The present invention provides also a composition for treating a masonry, comprising:

a fluorine-containing polymer which comprises

- (1) a fluoroalkyl group-containing monomer, and
- (2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the polymer, and

an organic solvent.

40 [0008] The present invention further provides a method of producing a treated masonry, which comprises applying said composition to a surface of a masonry, and then removing the solvent.

[0009] According to the present invention, a masonry having excellent water- and oil-repellency and soil resistance can be obtained.

### Mode for Carrying out Invention

45 [0010] The fluoroalkyl group-containing monomer is a compound having a fluoroalkyl group and a carbon-carbon double bond. Examples of the fluoroalkyl group-containing monomer are a (meth)acrylate monomer having a fluoroalkyl group, a maleate monomer having a fluoroalkyl group, and a fumarate monomer having a fluoroalkyl group. The fluoroalkyl group (Rf group) is preferably, for example, a perfluoroalkyl group, particularly a perfluoroalkyl group having 1  
50 to 21 carbon atoms, for example, 1 to 6 carbon atoms, especially 1 to 4 carbon atoms.

[0011] The fluoroalkyl group-containing (meth)acrylate monomer may be, for example, of the following formula:






55 wherein Rf is a fluoroalkyl group having 1 to 21, for example, 1 to 6 carbon atoms, R<sup>11</sup> is hydrogen or a methyl group, and A is a divalent organic group.

[0012] In the above formula, A is a linear or branched alkylene group having 1 to 20 carbon atoms, a -SO<sub>2</sub> N(R<sup>21</sup>)







R<sup>22</sup>- group or a -CH<sub>2</sub>CH(OR<sup>23</sup>)CH<sub>2</sub>-group (wherein R<sup>21</sup> is an alkyl group having 1 to 10 carbon atoms, R<sup>22</sup> is a linear or branched alkylene group having 1 to 10 carbon atoms, and R<sup>23</sup> is a hydrogen atom or acyl group having 1 to 10 carbon atoms).

[0013] Examples of the fluoroalkyl group-containing (meth)acrylate monomer include the followings:




wherein Rf is a fluoroalkyl group having 1 to 21 carbon atoms (for example, C<sub>4</sub>F<sub>9</sub>-, C<sub>8</sub>F<sub>17</sub>-), R<sup>1</sup> is hydrogen or an alkyl group having 1 to 10 carbon atoms, R<sup>2</sup> is an alkylene group having 1 to 10 carbon atoms, R<sup>3</sup> is hydrogen or a methyl group, Ar is an arylene group optionally having a substituent, and n is an integer of 1 to 10.



[0014] Specific examples of the fluoroalkyl group-containing (meth)acrylate monomer are as follows:





EP 1 568 721 A1




5





10





15




20





25





30




35





40




45













50






55





[n=1 to 12, particularly 1 to 10]





[0015] The amount of the fluoroalkyl group-containing monomer is generally from 50 to 98 % by weight, for example, from 60 to 80 % by weight, based on the polymer.











[0016] The the fluorine-containing polymer comprises the silicon-containing monomer.

[0017] The silicon-containing monomer is preferably a compound having a silane group (particularly terminal silane group) and a carbon-carbon double bond. The silicon-containing monomer may be a terminal silane coupling agent.

[0018] Specific examples of the silicon-containing monomer are as follows:



( $\gamma$ -methacryloxypropyltrimethoxysilane),



vinyltrichlorosilane, and

vinyl tris(2-methoxyethoxy)silane.

[0019] The amount of the silicon-containing monomer is 2.0 to 6.0 % by weight, based on the fluorine-containing polymer. If less than 2 % by weight, the water- and oil-repellency is poor. If more than 6 % by weight, the oil repellency is poor. The upper limit of the amount of the silicon-containing monomer may be 4.0 % by weight, for example, 3.5 % by weight, particularly 3.0 % by weight. The lower limit of the amount of the silicon-containing monomer may be 2.5 % by weight.

[0020] The fluorine-containing polymer may contain an other monomer in addition to the fluoroalkyl group-containing monomer and the silicon-containing monomer. The other monomer may be a fluorine-free monomer.

[0021] The fluorine-free monomer may be a fluorine-free alkyl (meth)acrylate.

[0022] The fluorine-free alkyl (meth)acrylate is generally a monomer of the formula:



wherein X is an alkyl carboxylate group (the number of carbon atoms in the alkyl group: 1 to 18), and X<sup>2</sup> is a hydrogen atom or a methyl group. The fluorine-containing polymer may not contain the fluorine-free alkyl (meth)acrylate.

[0023] The fluorine-containing polymer may contain other monomer other than fluorine-free monomer. Examples of the other monomer are Rf group-free monomers such as ethylene, vinyl chloride, vinylidene halide, styrene, acrylic acid and alkyl esters thereof, methacrylic acid and alkyl esters thereof, benzyl methacrylate, vinyl alkyl ketone, isoprene, chloroprene, maleic anhydride, butadiene, glycerol mono(meth)acrylate and glycidyl (meth)acrylate.

[0024] The amount of the other monomer may be from 0 to 100 parts by weight, for example, from 0 to 48 parts by weight, particularly from 1 to 40 parts by weight, based on 100 parts by weight of the fluoroalkyl group-containing monomer.

[0025] The fluorine-containing polymer can be prepared by any of conventional polymerization methods. The conditions of polymerization reaction can be arbitrarily selected. The polymerization procedure includes a bulk polymerization, a solution polymerization and an emulsion polymerization. The solution polymerization is generally preferable.

[0026] The molecular weight of the fluorine-containing polymer may be generally from 5,000 to 1,000,000 (for example, measured in GPC and in terms of polystyrene).

[0027] The treatment agent is in the form of a solution wherein the fluorine-containing polymer is dissolved in an organic solvent. The flash point of the organic solvent is preferably at least 65°C, for example, at least 70°C. The organic solvent may be an alcohol, an ester, a ketone or a halogenated hydrocarbon. The organic solvent may be a petroleum organic solvent.

[0028] In the treatment agent comprising the fluorine-containing polymer and the organic solvent, the concentration of the fluorine-containing polymer may be, for example, from 0.1 to 50 % by weight.

[0029] The treatment agent may contain an antifreezing agent, a viscosity-adjusting agent, an ultraviolet absorbing agent, an antioxidant, a pH adjuster, a defoaming agent, an antiseptic agent, a flame retardant, etc. according to necessity.

[0030] In the present invention, the treatment agent is applied to a substrate (masonry) to impart the water- and oil-repellency and the soil resistance to the substrate.

[0031] The substrate is masonry such as stone. Examples of the masonry include stone, brick, concrete and tile. Examples of stone include natural stone (for example, marble and granite), and artificial stone.

[0032] A method of treating the substrate is as follows. The treatment agent is applied to the substrate. The application can be performed by coating, dipping, brushing, etc. Then, the organic solvent is removed. The removal of the organic solvent can be performed by, for example, the drying. The drying can be performed at a temperature of, for example, 0 °C to 200 °C.

[0033] The application amount of the fluorine-containing polymer may be 0.05 to 50g, for example, 0.1 to 20g, especially 1 to 10g, per 1 m<sup>2</sup> of the surface area of the masonry.

[0034] The treatment agent can give the water-repellent oil-repellent performance to the masonry surface, since the treatment agent contains the fluorine-containing polymer. The adhesion of a soil to masonry can be prevented, even if the soil is an aqueous soil or is an oily soil.

#### Preferable Embodiments of Invention

[0035] Although Examples of this invention are described below, these are only examples of this invention and this invention is not limited thereto. Hereinafter parts and % are parts by weight and % by weight, unless specified.

## Preparative Example 1

[0036] Into a 500 cc four-necked flask equipped with a stirrer, an inert gas inlet, a condenser and a thermometer, 26.0 g of  $\text{CF}_3\text{CF}_2(\text{CF}_2\text{CF}_2)_n\text{CH}_2\text{CH}_2\text{OCOCH}=\text{CH}_2$  (a mixture of compounds wherein n is 3 and 4 in a weight ratio of 86:14), 13.0 g of stearyl acrylate, 1.0 g of  $\gamma$ -methacryloxypropyltrimethoxysilane (SZ6030 manufactured by Dow Corning Toray Co., Ltd.) and 120 g of butyl acetate were charged and heated to 70°C. 0.3 Grams of azobisisobutyronitrile was added and the polymerization reaction was conducted with stirring at 70°C for at least 12 hours. A gas chromatography revealed that a polymerization reaction conversion was at least 97%. The concentration of the polymer solution was adjusted to 25% with butyl acetate to give a solution of the polymer in butyl acetate.

## Comparative Preparative Example 1

[0037] Into the similar flask as in Preparative Example 1, 26.0 g of  $\text{CF}_3\text{CF}_2(\text{CF}_2\text{CF}_2)_n\text{CH}_2\text{CH}_2\text{OCOCH}=\text{CH}_2$  (a mixture of compounds wherein n is 3 and 4 in a weight ratio of 86:14), 14.0 g of stearyl acrylate and 120 g of butyl acetate were charged and heated to 70°C. 0.3 Grams of azobisisobutyronitrile was added and the polymerization reaction was conducted with stirring at 70°C for at least 12 hours. A gas chromatography revealed that a polymerization reaction conversion was at least 97%. The concentration of the polymer solution was adjusted to 25% with butyl acetate to give a solution of the polymer in butyl acetate.

## Comparative Preparative Example 2

[0038] Into the similar flask as in Preparative Example 1, 26.0 g of  $\text{CF}_3\text{CF}_2(\text{CF}_2\text{CF}_2)_n\text{CH}_2\text{CH}_2\text{OCOCH}=\text{CH}_2$  (a mixture of compounds wherein n is 3 and 4 in a weight ratio of 86:14), 12.0 g of stearyl acrylate, 2.0 g of  $\gamma$ -methacryloxypropyltrimethoxysilane (SZ6030 manufactured by Dow Corning Toray Co., Ltd.) and 120 g of butyl acetate were charged and heated to 70°C. 0.3 Grams of azobisisobutyronitrile was added and the polymerization reaction was conducted with stirring at 70°C for at least 12 hours. A gas chromatography revealed that a polymerization reaction conversion was at least 97%. The concentration of the polymer solution was adjusted to 25% with butyl acetate to give a solution of the polymer in butyl acetate.

## Example 1

[0039] Each of the polymer prepared in Preparative Example 1, a commercially available solvent-type fluorine-containing water- and oil-repellent agent, UNIDYNE TG-652 (manufactured by Daikin Industries, Co. Ltd.) and FORAPER-LE 225 (manufactured by Atofina) was diluted with mineral spirit to give a treatment liquid having the solid content of 3%.

[0040] A surface of each of polished natural granite (mined in China, and purchased from Nittai Kogyo Kabushiki-Kaisha) and limestone (purchased from Inax Corp.) was coated with the treatment liquid (1 mL of the treatment liquid was applied to an area of 5 cm x 10 cm). After left at room temperature for 10 minutes, a superfluous treatment liquid was wiped off. After left at room temperature for 24 hours, the following soil resistance test was conducted.

Soil resistance test method

[0041] A soil was put on an untreated or treatment agent-treated substrate, and droplets were left for 24 hours and wiped off with a paper towel. The evaluation was conducted according to the following criteria.

- 0 : Deep stain, and broad oil droplet spread
- 1 : Deep stain, and medium oil droplet spread
- 2 : Deep stain, and slight or no oil droplet spread
- 3 : Medium stain, and no spread
- 4 : Slight stain
- 5 : No stain.

[0042] The results are shown in Table 1 (granite) and Table 2 (limestone).



Table 1 (granite)

	Olive oil	Waste oil	Mustard	Ketchup	Red wine	Grape juice	Grapefruit juice	Soy sauce	Coffee	Aqueous ink (Blue)
Preparative Example 1	5	5	5	5	5	5	5	5	5	5
UNIDYNE TG-652	2	2	1	1	2	1	1	1	1	3
FORAPER LE 225	3	3	3	3	2	2	2	3	3	4
Untreated	1	1	1	1	1	1	1	1	1	1

Table 2 (Limestone)

	Olive oil	Waste oil	Mustard	Ketchup	Red wine	Grape juice	Grapefruit juice	Soy sauce	Coffee	Aqueous ink (Blue)
製造例1	5	5	5	5	5	5	5	5	5	5
UNIDYNE	2	2	4	4	1	2	3	4	3	2
TG-652										
FORAPER	5	4	5	5	2	3	3	4	3	2
LE 225										
Untreated	1	1	1	1	1	1	1	1	1	1

## Example 2

[0043] Each of the polymers obtained in Preparative Example 1, and Comparative Examples 1 and 2, UNIDYNE TG-652 (manufactured by Daikin Industries, Co., Ltd.) and FORAPERLE 225 (manufactured by Atofina) was diluted with mineral spirit to give a treatment liquid having the solid content of 3%.

[0044] A surface of each of polished natural granite (mined in China, and purchased from Nittai Kogyo Kabushiki-Kaisha) and limestone (purchased from Inax Corp.) was coated with the treatment liquid (1 mL of the treatment liquid was applied to an area of 5 cm x 10 cm). After left at room temperature for 10 minutes, a superfluous treatment liquid was wiped off. After left at room temperature for 24 hours, the same soil resistance test as in Example 1 was conducted.

[0045] The results are shown in Table 3 (granite) and Table 4 (limestone).

Table 3

(granite)				
	Olive Oil	Waste oil	Red wine	Coffee
Preparative Example 1	5	5	5	5
Comparative Preparative Example 1	4	4	3	4
Comparative Preparative Example 2	2	2	5	5
UNIDYNE TG-652	2	2	2	1
FORAPERLE 225	3	3	2	3
Untreated	1	1	1	1

Table 4

(limestone)				
	Olive Oil	Waste oil	Red wine	Coffee
Preparative Example 1	5	5	5	5
Comparative Preparative Example 1	3	4	3	3
Comparative Preparative Example 2	3	3	5	5
UNIDYNE TG-652	2	2	1	3
FORAPERLE 225	5	4	2	3
Untreated	1	1	1	1

## Example 3

[0046] Each of the polymer obtained in Preparative Example 1, UNIDYNE TG-652 (manufactured by Daikin Industries, Co., Ltd.) and FORAPERLE 225 (manufactured by Atofina) was diluted with a petroleum solvent (Shellisol D70) having a flash point of 73°C to give a treatment liquid having the solid content of 3%.

[0047] A surface of each of polished natural granite (mined in China, and purchased from Nittai Kogyo Kabushiki-Kaisha) and limestone (purchased from Inax Corp.) was coated with the treatment liquid (1 mL of the treatment liquid was applied to an area of 5 cm x 10 cm). After left at room temperature for 10 minutes, a superfluous treatment liquid was wiped off. After left at room temperature for 24 hours, the same soil resistance test as in Example 1 was conducted.

[0048] The results are shown in Table 5.

	Olive oil	Waste oil	Red wine	Coffee
Preparative Example 1	4	5	5	5
UNIDYNE TG-652	1	1	1	1
FORAPERLE 225	1	1	2	2
Untreated	1	1	1	1

Claims

1. A fluorine-containing polymer for treating a masonry, comprising:

- (1) a fluoroalkyl group-containing monomer, and  
(2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the polymer.

2. The fluorine-containing polymer according to claim 1, wherein the silicon-containing monomer is a compound having a silane group and a carbon-carbon double bond.

3. A composition for treating a masonry, comprising:

a fluorine-containing polymer which comprises

- (1) a fluoroalkyl group-containing monomer, and  
(2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the polymer, and

an organic solvent.

4. A method of producing a treated masonry, which comprises applying, to a surface of a masonry, a composition comprising:

a fluorine-containing polymer which comprises

- (1) a fluoroalkyl group-containing monomer, and  
(2) a silicon-containing monomer in the amount of 2.0 to 6.0 % by weight based on the polymer, and

an organic solvent, and then  
removing the solvent.

5. A masonry produced by the method according to claim 4.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/14184

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> Int.Cl. <sup>7</sup> C08F220/22, C09D133/16, C04B41/64		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) Int.Cl. <sup>7</sup> C08F220/22-220/24, C08L33/16, C09D133/16, C04B41/64, C09K3/18		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) WPI/L		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 2001-40211 A (JSR Corp.), 13 February, 2001 (13.02.01), Full text (Family: none)	1-5
X	JP 2-222471 A (Sanyo Chemical Industries, Ltd., Ishikawajima-Harima Heavy Industries Co., Ltd.), 05 September, 1990 (05.09.90), Full text (Family: none)	1-5
X	JP 11-507687 A (Minnesota Mining and Manufacturing Co.), 06 July, 1999 (06.07.99), Full text & WO 97/00230 A1                      & EP 832051 A1 & US 6037429 A	1,2,5
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed		"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family
Date of the actual completion of the international search 15 January, 2004 (15.01.04)		Date of mailing of the international search report 27 January, 2004 (27.01.04)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1998)